



INDUSTRIAL PAINT

INDUSTRIAL TECHNICAL DATA SHEET

S.N	PC.NO.	PRODUCTS	GLOSS	APPLICATION SYSTEM										PRODUCT DIScription																
				THINNER	THINNER INTAKE	HARDENER	HARDENER MIXING RATIO	BAKING TEMP.	APP. VIS.30°C	SURFACE DRY MINUTES	HANDALABALE MINUTE	HARD DRY HOUR	FULL CURED HOUR	D.F.T	PENTRATION	FILLING	DRYING TIME	INTER COAT ADDESION	CURING TIME	HANDABILITY	COVERAGE	SMOOTHNESS	INTERIOR	EXTERIOR	MAR RESISTANCE	CHEMICAL RESISTANCE	WEATHERABILITY	HEAT RESISTANCE	TEA/COFFEE RESISTANCE	HOT WATER RESISTANCE
QUICK DRYING INDUSTRIAL PRIMER Packing 20 ltr Price per ltr																														
1	303A	QD OIL PRIMER REDOXIDE	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			12h	30-40	A	A	B	B	B	B	A	A	A	B	C	C	C	B	C	B
2	303B	QD OIL PRIMER MIO	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			12h	30-40	A	A	B	B	B	B	A	A	A	B	C	C	C	B	C	B
3	303C	QD OIL PRIMER GREY	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	10m			12h	30-40	A	A	B	B	B	B	A	A	A	B	C	C	C	B	C	B
4	303U	QD HP PRIMER REDOXIDE	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			10h	30-40	A	A	B	A	B	B	A	A	A	B	C	C	C	B	C	B
5	303V	QD HP-PRIMER MIO	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			10h	30-40	A	A	B	A	B	B	A	A	A	B	C	C	C	B	C	B
6	303W	QD HP PRIMER GREY	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			10h	30-40	A	A	B	A	B	B	A	A	A	B	C	C	C	B	C	B
7	303D	QD PRIMER Z/C YELLOW	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			12h	30-40	A	A	B	B	B	B	A	A	A	B	C	C	C	B	C	B
8	303E	QD PRIMER Z/C REDOXIDE	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			12h	30-40	A	A	B	B	B	B	A	A	A	B	C	C	C	B	C	B
9	303F	ETCH PRIMER GREEN	1 to 2	303QD	20%	N/A	N/A	N/A	18 Sec	8m			30m	30-40	A	A	A	A	A	A	B	A	A	B	C	B	C	B	C	B
10	10	SPL PP PRIMER																												
QUICK DRYING INDUSTRIAL PAINTS Packing 20 ltr Price per ltr																														
11	303G	QD IND. GLOSSY CLEAR	100+	303QD	30%	N/A	N/A	N/A	16 Sec	20 m			48h	25-30	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
12	303H	QD IND. GLOSSY DA GREY	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
13	303I	QD IND. GLOSSY SIEMENS GREY	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
14	303J	QD IND. GLOSSY LIGHT BLUE	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
15	303K	QD IND. GLOSSY SUPER BLACK	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
16	303L	QD IND. GLOSSY TATA GOLDEN YELLOW	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
17	303M	QD IND. GLOSSY OPALINE GREEN	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
18	303S	QD IND. GLOSSY GOLDEN BROWN	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
19	303N	QD GLOSSY H/L BLACK	70-80	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
20	303O	QD GLOSSY H/L YELLOW	70-80	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
21	303P	QD GLOSSY H/L OPALINE GREEN	70-80	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
22	303Q	QD HAMMERTONE SILVER	-	303QD	30%	N/A	N/A	N/A	30 Sec	20 m			48h	-	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
23	303R	QD GLOSSY BRICK RED	90-95	303QD	30%	N/A	N/A	N/A	17 Sec	20 m			48h	30-35	A	A	B	A	B	B	A	A	B	A	B	B	A	B	A	A
STOVING PRIMERS, CLEARS & PAINT Packing 20 ltr Price per ltr																														
24	200A	STOVING GLOSSY CLEAR	105+	2020	30%	N/A	N/A	120°C	16 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
25	200B	STOVING CUM A/D INDUSTRIAL CLEAR	100+	2020	30%	N/A	N/A	120°C	17 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	B	B	A	B	A	A
26	200C	STOVING INDUSTRIAL EGGSHELL BLACK	20-25	2020	30%	N/A	N/A	120°C	17 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	B	B	A	B	A	A
27	202D	STOVING GLOSSY WHITE	90-95	2222	30%	N/A	N/A	120°C	17 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	A
28	202F	STOVING HAMMERTONE SILVER	-	2222	30%	N/A	N/A	120°C	17 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	B	B	A	B	A	A
29	200G	STOVING ACP JET BLACK	90-95		10%	N/A	N/A	120°C	30 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	B	B	A	B	A	A
30	201F	TSA CLEAR	105+		30%	N/A	N/A	150°C	16 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
31	201G	TSA SILVER	90+		30%	N/A	N/A	120°C	15 Sec	N/A			5h	40-50	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
EPOXY PRIMERS PACKING 25(20+(5X1)) Price per ltr WITH HARDENER																														
32	404A	EPOXY PRIMER REDOXIDE	4-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
33	404K	EPOXY PRIMER BLACK	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
34	404B	EPOXY PRIMER MIO	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
35	404C	EPOXY PRIMER GREY	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
36	404D	EPOXY Z/C PRIMER YELLOW	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A

37	404E	EPOXY DARK BUFF YELLOW PRIMER	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
38	404F	EPOXY SA PRIMER GREY	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
39	404G	EPOXY H.B ZINC RICH PRIMER GREY	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
40	404X	EPOXY Z/P PRIMER GREY	3-5	4141	25%	4949	4:1	N/A	18 Sec	20m			10h	40-50	A	A	B	A	A	B	A	B	A	B	C	A	B	B	A	A
EPOXY PAINTS PACKING 25(20+(5X1)) Price per ltr WITH HARDENER																														
41	404H	EPOXY S/G D.A GREY	50-55	4343	25%	4949	4:1	N/A	18 Sec	25m			12h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
42	404I	EPOXY S/G BUS GREEN	50-55	4343	25%	4949	4:1	N/A	18 Sec	25m			12h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
43	404J	EPOXY S/G SIEMENS GREY	50-55	4343	25%	4949	4:1	N/A	18 Sec	25m			12h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
44	404K	EPOXY S/G BLACK	50-55	4343	25%	4949	4:1	N/A	18 Sec	25m			12h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
45	404L	EPOXY S/G OXFORD BLUE	50-55	4343	25%	4949	4:1	N/A	18 Sec	25m			12h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
46	404M	EPOXY S/G TATA GOLDEN YELLOW	50-55	4343	25%	4949	4:1	N/A	18 Sec	25m			12h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
47	404N	EPOXY S/G SIGNAL RED	50-55	4343	25%	4949	4:1	N/A	18 Sec	25m			12h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
48	404O	EPOXY GLOSSY SMOKE GREY	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
49	404P	EPOXY GLOSSY LIGHT GREY	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
50	404Q	EPOXY GLOSSY OPALINE GREEN	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
51	404R	EPOXY GLOSSY SIEMENS GREY	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
52	404S	EPOXY GLOSSY JET BLACK	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
53	404T	EPOXY GLOSSY OXFORD BLUE	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
54	404U	EPOXY GLOSSY SIGNAL RED	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
55	404V	EPOXY GLOSSY NATURAL WHITE	100+	4343	30%	4848	4:1	N/A	17 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
56	404W	EPOXY GLOSSY CLEAR	100+	4343	30%	4848	4:1	N/A	16 Sec	25m			13h	30-40	A	A	B	A	A	B	A	A	A	B	A	A	B	B	A	A
5533 PU INDUSTRIAL PRIMERS PACKING 22(20+(2X1)) Price per ltr WITH HARDENER																														
57	5533A	PU PRIMER GREY	5-10	5533	25%	H-52	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	B	C	B	B	A	A	A
58	5533B	PU REDOXIDE PRIMER	5-10	5533	25%	H-52	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	B	C	B	B	A	A	A
59	5533C	PU BLACK PRIMER	5-10	5533	25%	H-52	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	B	C	B	B	A	A	A
60	5533D	PU YELLOW PRIMER	5-10	5533	25%	H-52	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	B	C	B	B	A	A	A
5533 PU INDUSTRIAL FINISHES PACKING 22(20+(2X1)) Price per ltr WITH HARDENER																														
61	5533E	PU S/G BLACK	50-55	5533	30%	H-52	10:1	N/A	17 Sec	15m			15h	30-40	A	A	A	A	A	A	A	A	A	B	A	B	B	A	A	A
62	5533F	PU SUPER BLACK FINISH	95+	5533	30%	H-52	10:1	N/A	17 Sec	15m			15h	30-40	A	A	A	A	A	A	A	A	A	B	A	B	B	A	A	A
63	5533G	PU YELLOW FINISH	95+	5533	30%	H-52	10:1	N/A	17 Sec	15m			15h	30-40	A	A	A	A	A	A	A	A	A	B	A	B	B	A	A	A
64	5533H	PU MATT BLACK	5-10	5533	30%	H-52	10:1	N/A	17 Sec	15m			15h	30-40	A	A	A	A	A	A	A	A	A	B	A	B	B	A	A	A
65	5533I	PU SIEMENS GREY	95+	5533	30%	H-52	10:1	N/A	17 Sec	15m			15h	30-40	A	A	A	A	A	A	A	A	A	B	A	B	B	A	A	A
5511 PU FLEXIBLE PRIMERS PACKING 22(20+(2X1)) Price per ltr WITH HARDENER																														
66	5511A	PU PRIMER GREY	5-10	5511	25%	H-62	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	A	C	A	A	A	A	A
67	5511B	PU PRIMER REDOXIDE	5-10	5511	25%	H-62	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	A	C	A	A	A	A	A
68	5511C	PU PRIMER BLACK	5-10	5511	25%	H-62	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	A	C	A	A	A	A	A
69	5511D	PU PRIMER YELLOW	5-10	5511	25%	H-62	10:1	N/A	18 Sec	10m			12h	30-40	A	A	A	A	A	A	A	B	A	A	C	A	A	A	A	A
5511 PU FLEXIBLE FINISHES PACKING 22(20+(2X1)) Price per ltr WITH HARDENER																														
70	5511E	PU CLEAR	110+	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
71	5511F	PU FINISH NATURAL WHITE	95	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
72	5511G	PU FINISH GREY WHITE RAL-9002	95	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
73	5511H	PU FINISH DEEP ORANGE	95	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
74	5511I	PU FINISH SUPER BLACK	95	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
75	5511J	PU FINISH BUS GREEN	95	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
76	5511K	PU FINISH SIGNAL RED	95	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
77	5511L	PU FINISH YELLOW	95	5511	30%	H-62	10:1	N/A	17 Sec	15m			12h	30-40	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
5588 HP PU PRIMERS PACKING 25(20+(5X1)) Price per ltr WITH HARDENER																														
78	5588A	HP PU PRIMER GREY	10-15	5511	25%	H-62	4:1	N/A	15 Sec	15m			10h	30-40	A	A	A	A	A	A	A	B	A	A	B	A	A	A	A	A
79	5588B	HP PU PRIMER REDOXIDE	5-10	5511	25%	H-62	4:1	N/A	15 Sec	15m			10h	30-40	A	A	A	A	A	A	A	B	A	A	B	A	A	A	A	A
80	5588C	HP PU PRIMER BLACK	10-15	5511	25%	H-62	4:1	N/A	15 Sec	15m			10h	30-40	A	A	A	A	A	A	A	B	A	A	B	A	A	A	A	A

